

<b>International Window 6260 3/4" Insulating Glass Unit Performance</b>												
<b>Horizontal Slide w/Steel Spacer</b>	<b>U-Factors</b>						<b>SHGC</b>			<b>Visible Light</b>		
	Air fill	With Argon	Sculptured Grid	Sculptured Grid with Argon	1/8" x 3/4" Grid	1/8" x 3/4" Grid with Argon		Sculptured Grid	1/8" x 3/4" Grid		Sculptured Grid	1/8" x 3/4" Grid
				with Argon							with Argon	
SS clear/ SS clear	0.66	0.65	0.66	0.65	0.66	0.65	0.69	0.56	0.62	0.72	0.57	0.64
DS clear/ DS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.67	0.54	0.60	0.71	0.57	0.64
3/16 clear/ 3/16 clear	0.68	0.65	0.70	0.68	0.69	0.66	0.64	0.52	0.58	0.70	0.56	0.62
SS EnergyShield™/ SS clear	0.52	0.48	0.52	0.48	0.52	0.48	0.33	0.27	0.30	0.61	0.49	0.55
DS EnergyShield™/ DS clear	0.52	0.48	0.54	0.49	0.52	0.48	0.33	0.27	0.30	0.61	0.48	0.54
3/16 EnergyShield™/ 3/16 clear	0.54	0.49	0.58	0.53	0.56	0.51	0.33	0.27	0.30	0.60	0.48	0.53
SS EnergyShield Xtreme™/ SS clear	0.51	0.48	0.51	0.48	0.51	0.48	0.24	0.20	0.22	0.54	0.44	0.49
DS EnergyShield Xtreme™/ DS clear	0.51	0.48	0.53	0.49	0.51	0.48	0.24	0.20	0.22	0.54	0.43	0.49
3/16 EnergyShield Xtreme™/ 3/16 clear	0.54	0.49	0.58	0.53	0.55	0.50	0.25	0.21	0.23	0.53	0.43	0.48
SS bronze/ SS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.55	0.45	0.50	0.53	0.42	0.47
DS bronze/ DS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.55	0.45	0.50	0.53	0.42	0.47
3/16 bronze/ 3/16 clear	0.68	0.65	0.70	0.68	0.69	0.66	0.49	0.40	0.44	0.46	0.36	0.41
1/4 Solarcool/ DS clear	0.68	0.65	0.71	0.67	0.69	0.65	0.28	0.23	0.26	0.16	0.13	0.15
DS grey/ DS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.51	0.42	0.46	0.47	0.38	0.43
3/16 grey/ 3/16 clear	0.68	0.65	0.70	0.68	0.69	0.66	0.45	0.36	0.40	0.39	0.31	0.35
DS greylite # 31/ DS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.28	0.23	0.26	0.19	0.15	0.17
SS Azuria/ SS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.43	0.35	0.39	0.61	0.49	0.55
DS Azuria/ DS clear	0.67	0.65	0.67	0.65	0.67	0.65	0.43	0.35	0.39	0.61	0.49	0.54
3/16 Azuria/ 3/16 clear	0.68	0.65	0.70	0.68	0.69	0.66	0.38	0.31	0.34	0.56	0.45	0.50
DS bronze/ DS EnergyShield™	0.52	0.48	0.54	0.49	0.52	0.48	0.33	0.27	0.30	0.45	0.36	0.40
3/16 bronze/ 3/16 EnergyShield™	0.54	0.49	0.58	0.53	0.56	0.51	0.30	0.25	0.27	0.39	0.31	0.35
DS grey/ DS EnergyShield™	0.52	0.48	0.54	0.49	0.52	0.48	0.31	0.25	0.28	0.40	0.32	0.36
3/16 grey/ 3/16 EnergyShield™	0.54	0.49	0.58	0.53	0.56	0.51	0.28	0.23	0.25	0.33	0.27	0.30
DS Azuria/ DS EnergyShield™	0.52	0.48	0.54	0.49	0.52	0.48	0.32	0.26	0.29	0.52	0.41	0.46
3/16 Azuria/ 3/16 EnergyShield™	0.54	0.49	0.58	0.53	0.56	0.51	0.30	0.25	0.27	0.48	0.38	0.43

U-Value is the overall coefficient of heat transmittance of heat flow measured in BTU/hr.\* ft2\*°F. Lower U-Values indicate better performance. Winter nighttime U-Values are calculated using an outdoor air temperature of 0°F and indoor air temperature of 70°F.

Solar Heat Gain Coefficient is defined that fraction of incident solar radiation that actually enters a building through the window as heat gain. The SHGC is expressed as a dimensionless number from 0 to 1.0 A high coefficient signifies high heat gain, while a low number means low heat gain.

Visible Transmittance is the amount of light in the visible portion of the spectrum that passes through a glazing material. This property does not directly affect heating and cooling loads in a building.

Clear glass - includes all non-tinted pattern glass, i.e. Obscure, Rain, Delta Frost

EnergyShield™ spectrally selective Low-E with emissivity 0.036

EnergyShield Xtreme™ spectrally selective Low-E with emissivity 0.024